

Brief Description:

COMBIMESH LGN-K is a bonded combination of a woven Mesh and a hot-needed perforated release film for the vacuum infusion process.

Technical Data:

		Unit	Value	Method
Area Weight	Hot needed film	g/m ²	40	LuV-Method
	Woven Mesh	g/m ²	180	
	Adhesive	g/m ²	max. 30	
Thickness	Hot needed film	mm	0.04	
	Woven Mesh	mm	1.00	
Peroration Diameter		mm	0.7	
Perforation	Distance	mm	8	
	Row Distance	mm	4	
	Misalignment	mm	4	
Perforated Area (Release film)		%	1.20	
Working Temperature		°C	max. 120	

Additional Information:

Delivery form	Hot needed film, blue, HDPE Woven Mesh, yellow, HDPE
Length	100 m
Width	max. 1,600 mm
Core Diameter	76 mm

Hazard Information: Store tightly closed and in a cool, well-ventilated area. Protect from humidity and direct sunlight. Detailed information in material safety data sheet.



The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Lehmann & Voss & Co. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein described materials or processes in violation of existing or future patents.

Lehmann&Voss&Co.
Alsterufer 19
20354 Hamburg
E-Mail: info@lehvoss.de
Internet: www.lehvoss.de

Contact:
Sales LUVATOL
Phone: +49/40/44 19 7 - 475
Fax: +49/40/44 19 7 - 478
luvaton@lehvoss.de

Lehmann&Voss&Co. 