

Brief Description:

VACUUM FILM PATS 215 is a high quality, heat stabilized cast Polyamide-Film for the vacuum infusion process.

Technical Data:

	Unit	Value	Method
Thickness	µm	50	
Density	g/ccm	1,125	
Use temperature	°C	max. 210	
Elongation at break MD/TD	%	min. 400 / 425	EN ISO 527-3

Additional Information:

Delivery form	Neutral color
Tolerance (thickness)	± 5 %
Tolerance (width)	± 1 %
Reel width	up to 3000 mm
Core diameter	76 / 152 mm
Storing instructions	Store VACUUM FILM PATS 215 dry in original packaging protected against UV-light (daylight). Ideal storage conditions are at a temperature of 20 °C and 60 % relative humidity.

Hazard Information: Store tightly closed and in a cool, well-ventilated area. Keep away from heat and sources of ignition. Detailed information in material safety data sheet.



The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Lehmann & Voss & Co. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein described materials or processes in violation of existing or future patents.

Lehmann&Voss&Co.
Alsterufer 19
20354 Hamburg
E-Mail: info@lehvoss.de
Internet: www.lehvoss.de

Contact:
Sales LUVATOL
Phone: +49/40/44 19 7 - 475
Fax: +49/40/44 19 7 - 478
luvaton@lehvoss.de

Lehmann&Voss&Co. 